



**Western Technologies Inc.**

The Quality People  
Since 1955

3737 East Broadway Road  
Phoenix, Arizona 85040-2921  
(602) 437-3737 • fax 470-1341

**LABORATORY REPORT**

Client **INTERNATIONAL CONSTRUCTION CHEMICALS INC**  
**ATTN: BILL BAILEY**  
**5620 OCEAN PINES CIRCLE**  
**LAS VEGAS NV 89130**

Date of Report **08-02-05**  
Job No. **2145XL307**  
Event / Invoice No. **Y307-01** Lab No. **1**  
Authorized By **ICCI/BAILEY** Date **07-27-05**  
Sampled By **ICCI** Date **07-19-05**  
Submitted By **COURIER** Date **07-27-05**

Project **LABORATORY SERVICES**  
Contractor **--**  
Type / Use of Material **ASPHALT CEMENT WITH EZ LIME**  
Sample Source / Location **LAB PREPARED MATERIAL INTO CIGAR \***  
Reference: **ASTM D 36**  
Special Instructions: **RING & BALL SOFTENING POINT**

Location **PHOENIX, ARIZONA**  
Arch. / Engr. **--**  
Supplier / Source **ICCI**  
Source / Location Desig. By **ICCI** Date **07-27-05**

**TEST RESULTS**

SAMPLE I.D.	TOP OF CIGAR TUBE SOFTENING POINT, °C	BOTTOM OF CIGAR TUBE SOFTENING POINT. °C
1	56.2	53.8
2 @ 350°F.	59.0	57.4
3	57.6	57.8
15% BW OIL @ ROOM TEMP.	59.0	58.2
15% BW OIL IN FREEZER	58.6	57.6

*pour & stored upright on shelf*

*72 hrs. @ 350°F oven upright*

*upright in freezer for 72 hrs.*

Comments: **\*TUBES BY OTHERS**

Copies To: **CLIENT (1)**

THE SERVICES REFERRED TO HEREIN WERE PERFORMED IN ACCORDANCE WITH THE STANDARD OF CARE PRACTICED LOCALLY FOR THE REFERENCED METHOD(S) AND RELATE ONLY TO THE CONDITION(S) OBSERVED OR SAMPLE(S) TESTED AT THE TIME AND PLACE STATED HEREIN. WESTERN TECHNOLOGIES INC. MAKES NO OTHER WARRANTY OR REPRESENTATION, EXPRESSED OR IMPLIED, AND HAS NOT CONFIRMED INFORMATION INCLUDING SOURCE OF MATERIALS SUBMITTED BY OTHERS.

REVIEWED BY *[Signature]*